



## SECTION 12485

### FOOT GRILLES, MATS, AND FRAMES

#### GENERAL

##### 1.1 SECTION INCLUDES

- A. Roll-up Mats.

##### 1.2 RELATED SECTIONS

- A. Section 03300 - Cast-In-Place Concrete.
- B. Section 06100 - Rough Carpentry.

##### 1.3 REFERENCES

- A. ASTM D 256 - Standard Test Method for Determining the Pendulum Impact Resistance of Notched Specimens of Plastics.
- B. ASTM D 635 - Standard Test Method for Rate of Burning and/or Extent and Time of Burning of Self-Supporting Plastics in a Horizontal Position.
- C. ASTM D 638 - Standard Test Method for Tensile Properties of Plastics.
- D. ASTM D 648 - Standard Test Method for Deflection Temperature of Plastics Under Flexural Load.
- E. ASTM D 696 - Standard Test Method for Coefficient of Linear Thermal Expansion of Plastics Between -30 degrees C and 30 degrees C.
- F. ASTM D 785 - Standard Test Method for Rockwell Hardness of Plastics and Electrical Insulating Materials.
- G. ASTM D 790 - Standard Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials.
- H. ASTM D 792 - Standard Test Methods for Density and Specific Gravity (Relative Density) of Plastics by Displacement.
- I. ASTM D 1784 - Standard Specification for Rigid Poly (Vinyl Chloride) (PVC) Compounds and Chlorinated Poly (Vinyl Chloride) (CPVC) Compounds.
- J. ASTM D 1822 - Standard Test Method for Tensile-Impact Energy to Break Plastic and Electrical Insulating Materials.
- K. ASTM D 2240 - Standard Test Method for Rubber Property--Durometer Hardness.
- L. ASTM D 3884 - Standard Test Method for Abrasion Resistance of Textile Fabrics (Rotary Platform, Double-Head Method).

- M. ASTM E 648 - Standard Test Method for Critical Radiant Flux of Floor-Covering Systems Using a Radiant Heat Energy Source.
- N. NFPA 253 - Standard Method of Test for Critical Radiant Flux of Floor Covering Systems Using a Radiant Heat Energy Source.
- O. UL 94V - Tests for Flammability of Plastic Materials for Parts in Devices and Appliances; Underwriters Laboratories Inc.

#### 1.4 SUBMITTALS

- A. Submit under provisions of Section 01300.
- B. Product Data: Manufacturer's product literature for products specified in this section.
- C. Shop Drawings: Indicate locations and dimension of recessed areas to receive products specified in this section.
- D. Selection Samples: For each specified product requiring color or finish selection, two sets of samples representing manufacturer's full range of available selections.
- E. Verification Samples: For each color or finish selected, two sets of samples indicating match to selected color or finish.
- F. Quality Assurance Submittals:
  - 1. Test Reports: Certified reports from independent testing laboratory supporting compliance of products to specified flammability requirements.
  - 2. Manufacturer's Instructions:
    - a. Printed installation instructions for each specified product.
    - b. Manufacturer's Safety Data Sheets (M.S.D.S.) for each adhesive.
- G. Closeout Submittals: Manufacturer's recommendations for cleaning and maintaining products specified in this section.

#### 1.5 QUALITY ASSURANCE

- A. Qualifications:
  - 1. Manufacturer: Minimum five (5) years documented experience producing products specified in this section.
  - 2. Installer: Minimum five (5) years documented experience installing products specified in this section, and approved by product manufacturer.

#### 1.6 DELIVERY, STORAGE, AND HANDLING

- A. Storage and Protection:
  - 1. Store products of this section in manufacturer's unopened packaging until installation.
  - 2. Maintain dry, heated storage area for products of this section until installation of products.
  - 3. Do not store outside.

#### 1.7 PROJECT/SITE CONDITIONS

- A. Field Measurements: Obtain field measurements of recessed areas to receive products of this section prior to order placement; include information on squareness and levelness of recess.

### PART 2 PRODUCTS

## 2.1 MANUFACTURERS

- A. Provide AL-TRACK 650 by **Amarco Products.**, PO Box 4085, 5 Powder Horn Drive, Warren, NJ, 07059; telephone 866-688-MATS (866-688-6287) or 732-302-1122; fax 1-877-MAT-ORDERS (877-628-6733) or 732-302-1120 ; [www.amarcoproducts.com](http://www.amarcoproducts.com)
- B. Requests for substitutions will be considered in accordance with provisions of Section 01600.
- C. Substitutions: Not permitted.
- D. Supply all products specified in this section from a single manufacturer.

## 2.2 MATERIALS

- A. Aluminum Metal: Alloy 6063-T6 conforming to ASTM B 221 and FS QQ-AA-200/9C.
- B. Aluminum Metal: Alloy 6105-T5 conforming to ASTM B 221.
- C. Bronze Metal: Alloy 385 conforming to ASTM B 455.
- D. Aluminum Metal: Alloy 6063-T5 conforming to ASTM B 221.
- E. Rigid Polyvinyl Chloride (PVC): Having the following physical characteristics:
  - 1. Cell classification, in accordance with ASTM D 1784: 16354.
  - 2. Specific gravity, when tested in accordance with ASTM D 792: 1.33.
  - 3. Tensile strength, when tested in accordance with ASTM D 638: 6,500 pounds per square inch.
  - 4. Modulus of elasticity, when tested in accordance with ASTM D 638: 400,000 pounds per square inch, average.
  - 5. Tensile impact, when tested in accordance with ASTM D 1822: 75 foot-pounds per square inch.
  - 6. Flexural strength, when tested in accordance with ASTM D 790: 12,500 pounds per square inch.
  - 7. Flexural modulus, when tested in accordance with ASTM D 790: 400,000 pounds per square inch.
  - 8. Izod impact, 1/8 inch, when tested in accordance with ASTM D 256: Minimum 20.
  - 9. Izod impact, 1/4 inch, when tested in accordance with ASTM D 256: Minimum 15.
  - 10. Hardness, Shore D, when tested in accordance with ASTM D 2240: 79.
  - 11. Hardness, Rockwell R, when tested in accordance with ASTM D 785: 108.
  - 12. Deflection temperature, when tested in accordance with ASTM D 648: 162 degrees F.
  - 13. Coefficient of thermal expansion, when tested in accordance with ASTM D 696: 0.00004 inch per inch per degree F.
  - 14. Flammability, when tested in accordance with UL 94V: 0.
- F. Nylon Carpeting:
  - 1. 100 percent solution dyed nylon fiber face with 1/4 inch finish pile height, 30 oz/sq yd, with yarn unitary fusion bonded to prevent fraying, delamination, and moisture penetration
  - 2. Flammability: Critical radiant flux 1.00 watts per square centimeter when tested in accordance with ASTM E 648 and NFPA 253 Radiant Panel Test; Class 1 rating.
- G. Nylon Carpeting:

1. Tufted cut pile 5/32 inch high, polyamide nylon 80 Dtex tetralobal fibers, 35 ounces per square yard weight, with 100 mil vinyl back coating.
  2. Carpet fiber weight loss maximum 1.3 percent when wear-tested in accordance with Taber Abraser method, ASTM D 3884, for 3000 cycles with H-10 wheel and 1000 gram weight.
  3. Flammability: Critical radiant flux 1.00 watts per square centimeter when tested in accordance with ASTM E 648 and NFPA 253 Radiant Panel Test; Class 1 rating.
- H. Polypropylene Bristle Filament Carpeting:
1. Tufted olefin fibers, 17-240 Dtex per filament, minimum 48 ounces per square yard weight, with UV stabilizers and pigments added before fiber extrusion
  2. Double needle vee-loop construction; rubber tile backed.
  3. Flammability: Department of Commerce FF-1-70 and FF-2-70.
- I. Rubber: Having the following physical characteristics:
1. Specific Gravity, when tested in accordance with ASTM D 792: 1.47, plus or minus 0.03.
  2. Tensile Strength, when tested in accordance with ASTM D 412: 650 psi
  3. Elongation, when tested in accordance with ASTM D 412: 550 %
  4. Durometer Shore A, when tested in accordance with ASTM D 224: 55, plus or minus 5.
  5. Tear Resistance, when tested in accordance with ASTM D 624: 75 pounds per inch.
  6. Temperature Stability Range: minus 30 degrees F to 120 degrees F.
  7. Shrinkage, after 7 days at 212 degrees F, when tested in accordance with ASTM D 1414: 2%
  8. Dielectric Strength, in accordance with MIL-M-155562: 37,000 volts.
  9. Conductivity: Non-Conductive.
  10. Flammability: Critical radiant flux 0.577 watts per square centimeter when tested in accordance with ASTM E 648 and NFPA 253 Radiant Panel Test; Class 1 rating.
- J. Rubber: Having the following physical characteristics:
1. Specific Gravity, when tested in accordance with ASTM D 792: 1.16, plus or minus 0.03.
  2. Tensile Strength, when tested in accordance with ASTM D 412: 1750 psi
  3. Elongation, when tested in accordance with ASTM D 412: 550%
  4. Durometer Shore A, when tested in accordance with ASTM D 224: 70, plus or minus 5.
  5. Tear Resistance, when tested in accordance with ASTM D 624: 235 pounds per inch.
  6. Compression Set, after 22 hours at 158 degrees F: 3%
  7. Brittleness, after 3 minutes at minus 40 degrees F: No cracks.
  8. Ozone Resistance, after 70 hours at 50 parts per hundred million ozone content, when tested in accordance with ASTM D 1149: No Trace.
  9. Flammability: Factory Mutual V-SS-302, and Department of Commerce FF 1-70.
- K. Polypropylene Carpeting:
1. Non-woven needle-punched, 100 percent solution dyed olefin fibers from Asota, 17-240 Dtex per filament, minimum 52 ounces per square yard weight, with UV stabilizers and pigments added before fiber extrusion.
  2. Double needle vee-loop construction; rubber tile backed.
  3. Carpet fiber weight loss maximum 2.7 percent when wear-tested in accordance with Taber Abraser method, ASTM D 3884, for 3000 cycles with

- H-10 wheel and 1000 gram weight.
  - 4. Flammability: Department of Commerce FF-1-70 and FF-2-70.
- L. Polypropylene Carpeting:
  - 1. Non-woven needle-punched, 100 percent solution dyed olefin fibers from Asota, 17-240 Dtex per filament, minimum 52 ounces per square yard weight, with UV stabilizers and pigments added before fiber extrusion.
  - 2. Double needle vee-loop construction; rubber tile backed.
  - 3. Carpet fiber weight loss maximum 3.8 percent when wear-tested in accordance with Taber Abraser method, ASTM D 3884, for 3000 cycles with H-10 wheel and 1000 gram weight.
  - 4. Flammability: Department of Commerce FF-1-70 and FF-2-70.
- M. Carpeting Adhesive: Non-flammable, and containing no toxic solvents; type recommended by manufacturer of products specified in this section.

### 2.3 ROLL-UP MATS

- A. Roll-up Mats: **AL-TRACK 650 Model AT-650.**
  - 1. Rails: Aluminum, extruded profile, assembled at 1-7/8 inches on center.
  - 2. Hinges: Extruded vinyl, perforated continuous hinge and support cushion, positively secured between aluminum rails; slotted perforations for drainage.
  - 3. Tread inserts: Corrugated aluminum (CA); extruded 1 inch wide, spaced 1-1/2 inches on center, crowned profile with four 1/8 inch flat corrugations per tread.
  - 4. Tread inserts: Aluminum with abrasive insert (AA); extruded 1 inch wide, spaced 1-1/2 inches on center, crowned profile with 13/16 inch abrasive mineral grit surface for slip resistance; minimum static coefficient of friction 1.14 dry, 1.20 wet.
  - 5. Tread inserts: Standard grade nylon carpet (SNC); inserts 1 inch wide, spaced 1-1/2 inches on center; 100 percent solution dyed nylon fiber face with 1/4 inch finish pile height, 30 oz/sq yd, with yarn unitary fusion bonded to prevent fraying, delamination, and moisture penetration; positively locked into rails.
  - 6. Tread inserts: Maxi-Tuft Long Wear nylon carpet (MLW); inserts 1 inch wide, spaced 1-1/2 inches on center; tufted, 5/32 inch pile, 100 percent polyamide nylon fibers with 100 mil vinyl backing; 35 oz/sq yd pile weight with 80 Dtex tetralobal fiber design, tufted at 78,000 fibers per square meter; minimum static coefficient of friction, 0.49 dry, 0.77 wet; treads positively secured into rails.
  - 7. Tread inserts: Bristle filament carpet (BF); inserts 1 inch wide, spaced 1-1/2 inches on center; 600 denier tufted polypropylene olefin stiff bristle carpet fibers tufted to rigid vinyl backing; minimum static coefficient of friction 0.49 dry, 0.77 wet.
  - 8. Tread inserts: Corrugated vinyl (RCV); rigid vinyl, 1 inch wide inserts, spaced 1-1/2 inches on center crowned profile with four 1/8 inch flat grooved corrugations per tread; flexible slip-resistant surface over rigid shrink resistant base.
  - 9. Overall depth: 5/8 inch.
  - 10. Colors: Selected from full range of manufacturer's standard colors.
  - 11. Colors:
    - a. Rails: \_\_\_\_\_.
    - b. Tread Inserts: \_\_\_\_\_.
  - 12. Colors: Specified in SCHEDULES Article of this section.
- B. Mat Edging: Manufacturer's standard vinyl edging as follows:

1. Profile: Bevel.
2. Profile: Square.
3. Color: Selected from full range of manufacturer's standard colors.
4. Color: \_\_\_\_\_.
5. Colors: Specified in SCHEDULES Article of this section.

C. Mat Frame:

1. Material: Aluminum extrusion.
2. Style: For recessed installation.
3. Style: For surface-mounted installation without nosing.
4. Profile: \_\_\_\_\_.
5. Finish: Selected from full range of manufacturer's standard colors.
6. Finish: \_\_\_\_\_.
7. Finish: Specified in SCHEDULES Article of this section.

## PART 3 EXECUTION

### 3.1 PREPARATION

- A. Verification of Conditions: Recesses to receive products of this section are correct size, are within square tolerances and level tolerances.
- B. Surface Preparation: Remove debris from recesses to receive frames; sweep recesses clean.

### 3.2 INSTALLATION

- A. Install specified products in accordance with shop drawings and manufacturer's printed installation instructions.

### 3.3 SCHEDULES

- A. Location: \_\_\_\_\_.
  1. Product: \_\_\_\_\_.
  2. Color: \_\_\_\_\_.
  3. Size: Indicated on drawings.

END OF SECTION

DISCLAIMER:

All statements, information, and data given herein are believed to be accurate and reliable, but are presented without guarantee, expressed or implied. Statements or suggestions concerning possible use of our products, including but not limited to the design of products and systems, are made without representation or warranty that any such use is free of patent infringement, and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required.

2007 American Mat & Rubber Company d/b/a/ Amarco Products. All Rights Reserved.  
A copyright license to reproduce this specification is hereby granted  
to non-manufacturing architects, specification writers, and designers.

Rev 7/07