

## Foot-Ease – 1/2" Rubber Surfaced

### Anti-Fatigue Matting

#### Technical Data

#### Product Description

- **Materials:** Marbleized surface combined with dense closed cell foam base
- **Thickness:** 1/2"
- **Mat Sizes:** 18" x 30" / 18' x 48' / 2' x 3' / 3' x 5'
- **Roll Sizes:** 2' x 60' / 3' x 60' / 4' x 60'

| Criteria                         | Test       | Result                     |
|----------------------------------|------------|----------------------------|
| Weight                           | --         | 2 lbs/ft <sup>2</sup>      |
| Tensile Strength                 | ASTM D412  | 1464 lbs / in <sup>2</sup> |
| Tear Strength                    | ASTM D624  | 51 kN/m                    |
| Elongation                       | ASTM D412  | 261                        |
| Durometer                        | ASTM D2240 | 75-80                      |
| Specific Gravity                 | ASTM D792  | 1.35-1.40                  |
| Resistance to Chemicals / Fluids |            |                            |
| Acetic Acid                      |            | 1 – No Effect              |
| Acetone                          |            | 2 – Negligible Effect      |
| Animal Fats                      |            | 2 – Negligible Effect      |
| Brake Fluid                      |            | 2 – Negligible Effect      |
| Butyl Alcohol                    |            | 2 – Negligible Effect      |
| Chlorine Wet                     |            | 2 – Negligible Effect      |
| Cutting Fluid (wb)               |            | 2 – Negligible Effect      |
| Cutting Fluid (so)               |            | 3 – Moderate Effect        |
| Diesel Oil                       |            | 2 – Negligible Effect      |
| Gasoline                         |            | 2 – Negligible Effect      |
| Mineral Oil                      |            | 2 – Negligible Effect      |
| Nitric Acid                      |            | 1 – No Effect              |
| Sodium Hydroxide                 |            | 2 – Negligible Effect      |
| Sulfuric Acid                    |            | 1 – No Effect              |
| Toluene                          |            | 2 – Negligible Effect      |
| Transmission Fluid               |            | 2 – Negligible Effect      |
| Trichlorthane                    |            | 3 – Moderate Effect        |
| Vegetable Oil                    |            | 1 – No Effect              |